



## Surfit™ 1345

### Manufacturing Process

Gas Atomised


Origin: Belgium

Article No. 115998

### Features & Benefits

machines well  
recommended as  
build up layers

### Flame Spray - Ni base



Published March 2010 by Höganäs AB

Höganäs AB (publ.) | SE-263 83 Höganäs | Sweden | [www.hoganas.com](http://www.hoganas.com)

For more information about Surfit™ [www.hoganasthermalspray.com](http://www.hoganasthermalspray.com) | [info@hoganasthermalspray.com](mailto:info@hoganasthermalspray.com)

## Product Data Sheet

### Application Properties

Hardness

Fusing-Temperature

Min

42

1000

Max

46

1030

Unit

HRC

°C

### Physical Properties

Apparent Density

Flow

### Typical Values

4,6

14,9

Unit

g/cm<sup>3</sup>

s/50g

### Chemical Analysis

Fe

C

Si

B

Ni

Cr

Min

2,00

0,30

3,30

1,70

balance

7,50

Max

3,40

0,40

3,90

2,00

10,0

Unit

%

%

%

%

%

### Sieve Analysis

µm

Mesh

+150

+100

+125

+120

45-125

-45

-325

### Product Specifications

Min

balance

Max

0,00

4,00

3,00

Unit

%

%

%

### Standard Packaging

Bottle

5 kg