



## Surfit™ 1360

### Manufacturing Process

Gas Atomised


Origin: Belgium

Article No. 115954

### Features & Benefits

high wear & corrosion  
medium impact resistance  
recommended carbide tools  
for machining & grinding

### Flame Spray - Ni base



### Application Properties

Hardness

Fusing-Temperature

### Physical Properties

Apparent Density

Flow

### Chemical Analysis

Fe

C

Si

B

Ni

Cr

### Sieve Analysis

µm	Mesh
+ 150	+100
+ 125	+120
45-125	
-45	-325

### Standard Packaging

Bottle 5 kg

## Product Data Sheet

Min	Max	Unit
59	63	HRC
980	1020	°C

Typical Values	Unit
4,4	g/cm <sup>3</sup>
15,0	s/50g

Product Specifications		
Min	Max	Unit
2,40	4,60	%
0,65	0,80	%
3,90	4,90	%
3,00	3,40	%
balance		
14,00	16,00	%

Product Specifications		
Min	Max	Unit
	0,00	%
	4,00	%
balance		
	3,00	%